



ASPELAND

PRODUCT DETAILS

Article Number	151NDSEK01KW240
EAN Code	7393969039024
Surface Treatment	Oil This floor should be oiled immediately after installation.
Dimensions	95 1/4 x 7 3/8 x 5/8"
Weight per Package	48.5 lbs
Area per Package	29.1 sqft
Area per pallet (m²)	1317.5 sqft
Package info	Packages may contain start and stop boards.

DETAIL DESCRIPTION

All naturally occurring wood colour variations allowed, from light to dark brown. Sapwood may occur. The product includes very large sound and black knots and cracks. Knots and cracks will be present in all sizes and numbers.

COLOR CHANGE

Stained product - noticeable color change over time.

FACTS

Design	1-strip
Grading	Expressive
Range	Kährs Supreme
Collection	Småland Collection
Resandable	2 times
Natural/Stained	Stained
Brinell Value	3,7
Joint	Woodloc® 5S
Floor heating	Yes
	30 years
Wear-layer material	Hardwood
Core material	Pine/Spruce lamella
	5/8"
Installation method	Floating, Glue-Down
Installation method	Floating, Glue-Down

TECHNICAL PROPERTIES

Moisture content	EN13183	7%±2%
Minimum Mean Density kg/m³	>500 kg/m ³	
Reaction To Fire	EN13501-1	Dfl-s1
Formaldehyde Emission	EN717-1	E1
Content PCP	CEN/TR14823	≤ 5 x 10 ⁻⁶ n
Breaking Strength N/mm²	EN1533	NPD
Thermal Conductivity	EN12664	0,14 W/mK
Thermal Resistance R-Value	.11 (m ² K/W)	
Biological Durability	EN350-2	Class 1
CARB2	Compliant	


Other products in this collection



Oak Klinta



Kinda



Sevede




Ydre



Möre



Vista



Vedbo



Handbörd



Tveta



Finnveden



Aspeland

CERTIFICATES



Descriptions & Imagery

All samples, images and product description, plus photo and brochure specifications are there for the sole purpose of giving an approximate idea of the items described in them. They shall not form part of the contract or have any contractual force and should be viewed for illustrative purposes only. We cannot guarantee that your computer's display or the quality of the print will accurately reflect the colour of the products. Your product may vary slightly from the images within this literature.