

Model: THAO VERBIER SAND 59,6X59,6(A)

Codes: 100278671

Water absorption: Bla - Porcelánico ( $E \leq 0.1\%$ )



MATE / MATT



DETONIFICADO  
TONE VARIATIONS



RECTIFICADO  
RECTIFIED



## DIMENSIONAL FEATURES

UNE-EN ISO 10545-2

Thickness	10.5 MM	+/-5%*
Width	596 MM	
Length	596 MM	
Length and width deviation	Below 0.15%	+/-0.3%*
Side straightness deviation	Below 0.15%	+/-0.3%*
Squareness deviation	Below 0.15%	+/-0.3%*
Surface flatness deviation	Below 0.15%	+/-0.4%*

\*ISO-13006:2018 UNE-EN 14411:2016

## MECHANICAL FEATURES

UNE-EN ISO 10545-4-6-7-11

Breaking strength	2710 N	>1300N*
Modulus of rupture	51 N/MM2	>=35N/mm2*
Crazing resistance	Resists 3 cycles	

\*ISO-13006:2018 UNE-EN 14411:2016

## HYGIENIC FEATURES

UNE-EN ISO 10545-13-14:1995

Chemical resistance	Class "A" for swimming pools and cleaning products (resists attack). Minimum Class "B" for acids and bases	B Min.*
Stain resistance	Class 5. Easy cleaning with water	3 Min.*

\*ISO-13006:2018 UNE-EN 14411:2016

## SCOPE OF USE

Technical code-1	Use on walls	
------------------	--------------	--

## ANTI-SLIP VALUE

UNE 41901:2017 EX, UNE 41902:2017 EX, DIN-51130 y ASTM C1028

Slip resistance (dcof)	No Aplica	
------------------------	-----------	--

\*ISO-13006:2018 UNE-EN 14411:2016

## PACKING

Sales units per box	1.4209 M2/BOX	
Sales units per pallet	45.4675 M2/PAL	
Sales units per unit	0.3552 M2/PIECE	

System Certification



Do not use cleaning agents containing hydrofluoric acid.

It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint.

For big sizes, it is recommended to fix with mortars containing polymeric additives and to use the double gluing technique.

Mosaic tiles must be grouted.

This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.