## L'OC PORCELANOSA Grupo

Model: AC4 RESIDENCE 1L MISURI Codes: 100201397 - L167012882 Group: G-200 Format: 19,3X138X0,8 Thickness: 8 mm



|  |         | CO                     | MPOSITI        | ON   |  |  |  |
|--|---------|------------------------|----------------|--|--|--|--|
|  |         |                        | Material       | Type of material   |  |  |  |
|  | Layer 1 | 0.2                    | Melamine       | Aminoplastic thermosetting resins  |  |  |  |
|  | Layer 2 | 0.2                    | Decorative pap | ber  |  |  |  |
|  | Layer 3 | 7.5 H                  | HDF            | High-density Fiber Board and water-repellent glues   |  |  |  |
|  | Layer 4 | E                      | Backside       | Sheets of kraft paper impregnated with phenolic resins   |  |  |  |
|  |         | CER                    | TIFICATIO      |  |  |  |  |
| Carb certification   |         | CARB: Phase II complia |                |  |  |  |  |
| carb certification   |         |                        |                |  |  |  |  |
|  |         | F                      | EATURES        | 5  |  |  |  |
| Imitates the surface of wood   |         |                        | $\oplus$       | Beveled cut on all 4 edges of the board for emphasizing size   |  |  |  |
| Gloss-free   |         |                        | $\mathbf{O}$   | Installation system where gluing the boards to the floor is not necessary. They are installed on a foam and joined together  |  |  |  |
| 20 year warranty for domestic use valid for laminate floors that have been installed in rooms where they are exposed to normal wear and tear for their recommended End Use Category in accordance with EN 13329. |         |                        | ir 5           | 5 year warranty for commercial use valid for laminate floors that have been installed in rooms where they are exposed to normal wear and tear for their recommended End Use Category in accordance with EN 13329.  |  |  |  |
| Format where only one board has been used to finish the entire base surface  |         |                        | ce 📛           | Is suitable for installing on water radiant heating  |  |  |  |
| Floor capable of dissipating excess electrical charges and distribute them over its entire surface   |         |                        | ver its        | It is one of the easiest to install and safest systems in the market. We just need to adjust the board to be installed longitudinally to the one already placed, by applying a soft pressure without the need for any type of tool. Both pieces will fir and will be secured thanks to the safety tab. It is just as simple to take apart, which makes for a quick disassembly |  |  |  |
| 23. Intensive residential  |         |                        | T m            | 32. General commercial   |  |  |  |
| AC4 Abrasion-resistance level as per Standard UNE-EN 13329   |         |                        |                |  |  |  |  |
| 0  |         |                        |                |  |  |  |  |



## L'OC PORCELANOSA Grupo

## DIMENSIONAL FEATURES

| Difference in height among items                               | ≤0.15 mm  | EN 13329*         |  |  |  |
|--|---|-------------------|--|--|--|
| Dimensional variations related to changes in relative moisture | ≤0.90 mm  | EN 13329*         |  |  |  |
| Flatness of item (f)   | fw,Cóncavo≤0.50% fw,Convexo≤1%/fl,Cóncavo≤0.15%<br>fl,Convexo≤0.20% | EN 13329*         |  |  |  |
| Item thickness   | ≤0.50 mm  | EN 13329*         |  |  |  |
| Joint between items  | ≤0.20 mm  | EN 13329*         |  |  |  |
| Length of face   | ≤0.50 mm  | EN 13329*         |  |  |  |
| Punching   | No visible changes  | EN 433*           |  |  |  |
| Squareness of the item (q)                                     | ≤0.20 mm  | EN 13329*         |  |  |  |
| Straightness of face   | ≤0.30 mm/m  | EN 13329*         |  |  |  |
| Surface stripping  | ≥1.00 N/mm2   | EN 13329 Anexo D* |  |  |  |
| Uv light fastness  | ≥4  | EN 438-2,16*      |  |  |  |
| Width of face  | ≤0.20 mm  | EN 13329*         |  |  |  |

| LABORATORY TESTS  |                                   |                    |  |  |  |  |
|---|-----------------------------------|--------------------|--|--|--|--|
| Castor chair effect   | No damage                         | EN 425*            |  |  |  |  |
| Density of the board  | 840±5 KG/M3                       | UNE EN 323*        |  |  |  |  |
| Evaluation of propensity to accumulation of electrostatic charges | ≤2 kV                             | EN 1815*           |  |  |  |  |
| Fire resistance   | Cfl-s1                            | EN 13501*          |  |  |  |  |
| Formaldehyde emissions  | E1                                | DIN EN 120*        |  |  |  |  |
| Furniture leg effect  | No damage                         | EN 424*            |  |  |  |  |
| Heat resistance   | 0.065 M2*°K/W                     | UNE-EN 12667*      |  |  |  |  |
| Impact resistance   | IC2                               | UNE EN 13329*      |  |  |  |  |
| Resistance to abrasion  | AC4                               | UNE EN 13329:2000* |  |  |  |  |
| Resistance to cigarette burns                                     | 4                                 | EN 438*            |  |  |  |  |
| Resistance to microscratching                                     | Class 1                           | EN 16094*          |  |  |  |  |
| Resistance to staining  | Grado 5 (G 1 y 2) y Grado 4 (G 3) | EN 438*            |  |  |  |  |
| Slip resistance (dcof)  | Clase DS                          | EN 14041*          |  |  |  |  |
| Swelling in thickness   | ≤18%                              | ASTM D 1037*       |  |  |  |  |
| Swelling in thickness   | ≤18%                              | UNE-EN 13329*      |  |  |  |  |
| Tensile strength of joints  | >1.0 MPA                          | EN 13329*          |  |  |  |  |
| Thermal conductivity  | 0.123 W/M*°K                      | UNE-EN 12667*      |  |  |  |  |

|               | PACKING         |  |
|---------------|-----------------|--|
| Base unit     | PIECES          |  |
| Boxes         | 2.1307 M2/BOX   |  |
| Gross weight  | 7.4679 KG/M2    |  |
| Net weight    | 7.2802 KG/M2    |  |
| Pallets       | 119.3203 M2/PAL |  |
| Sale unit     | M2              |  |
| Square meters | 1 M2            |  |
| Units         | 0.2663 M2/PIECE |  |

|           | SPECIAL PIECES |   |       |          |             |            |     |            |            |              |
|-----------|----------------|---|-------|----------|-------------|------------|-----|------------|------------|--------------|
| SAP       | KEA            | Description                             | Group | Boxes    | Pallet      | Units      | SKU | Basic Unit | Net Weight | Gross weight |
| 100202645 | L167012886     | IGUALACION RESIDENCE MISURI 4X270X1     | G-155 | 20 ST/CS | 1000 ST/PAL | 9.31 ST/M2 | ST  | ST         | 0.68 KG/ST | 0.7 KG/ST    |
| 100202653 | L167012891     | MAMPERLAN AC4 RESIDENCE 1L MISURI 120X7 | G-163 | 2 ST/CS  | 200 ST/PAL  | 11.9 ST/M2 | ST  | ST         | 1.58 KG/ST | 1.64 KG/ST   |
| 100202660 | L167012896     | TRANSICION RESIDENCE MISURI 4X270X1     | G-155 | 20 ST/CS | 1000 ST/PAL | 9.26 ST/M2 | ST  | ST         | 0.7 KG/ST  | 0.72 KG/ST   |
| 100202656 | L167012901     | ZOCALO RESIDENCE MISURI 8X220X1,5       | G-107 | 14 ST/CS | 560 ST/PAL  | 5.68 ST/M2 | ST  | ST         | 1.8 KG/ST  | 1.86 KG/ST   |

