

Model: AC4 STYLE 1L PACIFIC
Codes: 100289642 - L167013395
Group: G-204
Format: 19,2X126,1X0,7
Thickness: 7 mm



COMPOSITION














| | Size | Material | Type of material |
|---------|------|------------------|--|
| Layer 1 | 0.2 | Melamine | Aminoplastic thermosetting resins |
| Layer 2 | 0.1 | Decorative paper | |
| Layer 3 | 6.6 | HDF | High-density Fiber Board and water-repellent glues |
| Layer 4 | 0.1 | Backside | Sheets of kraft paper impregnated with phenolic resins |

CERTIFICATIONS

| | |
|--------------------|---|
| Carb certification | US EPA TSCA Title VI and CARB Phase 2 compliant |
|--------------------|---|

FEATURES

-  Imitates the surface of wood
-  Installation system where gluing the boards to the floor is not necessary. They are installed on a foam and joined together
-  20 20 year warranty for domestic use valid for laminate floors that have been installed in rooms where they are exposed to normal wear and tear for their recommended End Use Category in accordance with EN 13329.
-  5 5 year warranty for commercial use valid for laminate floors that have been installed in rooms where they are exposed to normal wear and tear for their recommended End Use Category in accordance with EN 13329.
-  Format where only one board has been used to finish the entire base surface
-  Is suitable for installing on water radiant heating
-  PanEuropean Forest Certification that guarantees to consumers the origin of the products from sustainably managed forests
-  Safety and joint durability are the main features of this easy installation system that guarantees the elimination of gaps between boards throughout the floor's lifetime. The pressure exerted between boards reinforces the union and prevents it from being carried out incorrectly.
-  23. Intensive residential
-  32. General commercial
-  AC4 Abrasion-resistance level as per Standard UNE-EN 13329

DIMENSIONAL FEATURES

| | | |
|--|--|-------------------|
| Difference in height among items | ≤0.15 mm | EN 13329* |
| Dimensional variations related to changes in relative moisture | ≤0.90 mm | EN 13329* |
| Flatness of item (f) | fw,Cóncavo≤0.50% fw,Convexo≤1%/fl,Cóncavo≤0.15% fl,Convexo≤0.20% | EN 13329* |
| Item thickness | ≤0.50 mm | EN 13329* |
| Joint between items | ≤0.20 mm | EN 13329* |
| Length of face | ≤0.50 mm | EN 13329* |
| Punching | No visible changes | EN 433* |
| Squareness of the item (q) | ≤0.20 mm | EN 13329* |
| Straightness of face | ≤0.30 mm/m | EN 13329* |
| Surface stripping | ≥1.00 N/mm ² | EN 13329 Anexo D* |
| Uv light fastness | 7 | EN 438-2,16* |
| Width of face | ≤0.20 mm | EN 13329* |

LABORATORY TESTS

| | | |
|---|-----------------------------------|--------------------|
| Castor chair effect | No damage | EN 425* |
| Critical radiant flux | Cfl | EN ISO 9239-1* |
| Density of the board | 890 ±5 KG/M ³ | UNE EN 323* |
| Dimensional stability | Max≤0.15 mm | EN 13329* |
| Evaluation of propensity to accumulation of electrostatic charges | ≤2 kV | EN 14041* |
| Fire resistance | Cfl-s1 | EN 13501* |
| Formaldehyde emissions | E1 | EN 717* |
| Furniture leg effect | No damage | EN 424* |
| Heat resistance | R=0.046 m ² K/W | ISO 8302-1991* |
| Impact resistance | IC2 | UNE EN 13329* |
| Moisture upon leaving factory | 4%-10% | |
| Resistance to abrasion | AC4 | UNE EN 13329:2000* |
| Resistance to cigarette burns | 4 | EN 438* |
| Resistance to staining | Grado 5 (G 1 y 2) y Grado 4 (G 3) | EN 438* |
| Slip resistance (cls) | Clase DS | EN 13893* |
| Slip resistance (dcof) | Class DS:≥0.30 | EN 13893* |
| Smoke density (burning) | s1 | EN 13501-1* |
| Swelling in thickness | ≤18% | ASTM D 1037* |
| Swelling in thickness | ≤18% | UNE-EN 13329* |
| Tensile strength of joints | >1.0 N/mm ² | EN 13329* |

PACKING

| | | |
|---------------|--------------------------|--|
| Base unit | PIECES | |
| Boxes | 2.4211 M2/BOX | |
| Gross weight | 6.7242 KG/M ² | |
| Net weight | 6.5383 KG/M ² | |
| Pallets | 125.8982 M2/PAL | |
| Sale unit | M2 | |
| Square meters | 1 M2 | |
| Units | 0.2421 M2/PIECE | |

SPECIAL PIECES

| SAP | KEA | Description | Group | Boxes | Pallet | Units | SKU | Basic Unit | Net Weight | Gross weight |
|-----------|------------|--|-------|----------|-------------|-------------------------|-----|------------|------------|--------------|
| 100297558 | L167013463 | IGUALACION STYLE PACIFIC 4X270X1 | G-155 | 20 ST/CS | 1000 ST/PAL | 92.59 ST/M ² | ST | ST | 0.77 KG/ST | 0.8 KG/ST |
| 100297565 | L167013436 | MAMPERLAN AC4 STYLE 1L PACIFIC 120X7X3 | G-163 | 2 ST/CS | 200 ST/PAL | 11.9 ST/M ² | ST | ST | 1.58 KG/ST | 1.64 KG/ST |
| 100297564 | L167013431 | TRANSICION STYLE PACIFIC 4X270X1 | G-155 | 20 ST/CS | 1000 ST/PAL | 92.59 ST/M ² | ST | ST | 0.77 KG/ST | 0.8 KG/ST |
| 100297573 | L167013433 | ZOCALO STYLE PACIFIC 8X220X1,5 | G-107 | 14 ST/CS | 560 ST/PAL | 5.68 ST/M ² | ST | ST | 1.8 KG/ST | 1.86 KG/ST |